Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID	:	**CP-2018-04-21-03** **Date: 26/04/2018**
Customer	:	Assistant Executive Engineer, Byatarayanapura Sub Division, BBMP, Bangalore.
Address	:	Byatarayanapura Sub Division, BBMP, Bangalore.
Project Name	:	Improvements of roads and drains at Sandeep UnniKrishnan Nagar in Ward No.05, Byatarayanapura Sub Division.
Agency	:	Y.B. Ramesh, No.34, Down Bazar road, Yelahanka, Bangalore-64
Customer's Reference	:	EE/BTP/BBMP/E-PMT/194/2015-16
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	21-04-18
Sample ID No	:	2018-04-21-03 /05
Customer ID	:	RCC
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M20 / 7 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	26/04/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	RCC	M20	19/04/2018	26/04/2018	151.11 X 150.38 X 150.03	22724	8.395	428.2	18.8	18.6
2	RCC	M20	19/04/2018	26/04/2018	151.64 X 149.36 X 149.39	22649	8.279	429.3	19.0	
3	RCC	M20	19/04/2018	26/04/2018	150.66 X 151.91 X 150.62	22886	8.158	414.6	18.1	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL Pro Sig..... Date..... BANGALORE

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: TC- 5548

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-04-21-03** **Date: 17/05/2018**

Customer : Assistant Executive Engineer, Byatarayanapura Sub Division, BBMP, Bangalore.

Address : Byatarayanapura Sub Division, BBMP, Bangalore.

Project Name : Improvements of roads and drains at Sandeep UnniKrishnan Nagar in Ward No.05, Byatarayanapura Sub Division.

Agency : Y.B. Ramesh, No.34, Down Bazar road, Yelahanka, Bangalore-64

Customer's Reference : EE/BTP/BBMP/E-PMT/194/2015-16

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 21-04-18

Sample ID No : 2018-04-21-03 /06

Customer ID : RCC

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M20 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 17/05/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	RCC	M20	19/04/2018	17/05/2018	149.62 X 150.30 X 149.66	22488	8.518	431.4	19.2	19.8
2	RCC	M20	19/04/2018	17/05/2018	150.18 X 149.09 X 149.96	22391	8.355	431.8	19.3	
3	RCC	M20	19/04/2018	17/05/2018	151.24 X 149.44 X 150.22	22601	8.545	474.4	21.0	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

CIVIL PRO Sig..... Date..... BANGALORE

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-04-21-03** **Date: 26/04/2018**

Customer : Assistant Executive Engineer, Byatarayanapura Sub Division, BBMP, Bangalore.

Address : Byatarayanapura Sub Division, BBMP, Bangalore.

Project Name : Improvements of roads and drains at Sandeep UnniKrishnan Nagar in Ward No.05, Byatarayanapura Sub Division.

Agency : Y.B. Ramesh, No.34, Down Bazar road, Yelahanka, Bangalore-64

Customer's Reference : EE/BTP/BBMP/E-PMT/194/2015-16

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 21-04-18

Sample ID No : 2018-04-21-03 /03

Customer ID : RCC

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M20 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 26/04/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	RCC	M20	19/04/2018	26/04/2018	149.28 X 150.25 X 151.01	22430	8.144	416.3	18.6	18.5
2	RCC	M20	19/04/2018	26/04/2018	149.63 X 151.17 X 151.24	22620	8.145	415.0	18.3	
3	RCC	M20	19/04/2018	26/04/2018	151.93 X 151.90 X 149.19	23079	8.141	431.8	18.7	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL PRO Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Page 1/1
****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-04-21-03** **Date: 17/05/2018**

Customer : Assistant Executive Engineer, Byatarayanapura Sub Division, BBMP, Bangalore.

Address : Byatarayanapura Sub Division, BBMP, Bangalore.

Project Name : Improvements of roads and drains at Sandeep UnniKrishnan Nagar in Ward No.05, Byatarayanapura Sub Division.

Agency : Y.B. Ramesh, No.34, Down Bazar road, Yelahanka, Bangalore-64

Customer's Reference : EE/BTP/BBMP/E-PMT/194/2015-16

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 21-04-18

Sample ID No : 2018-04-21-03 /04

Customer ID : RCC

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M20 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 17/05/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	RCC	M20	19/04/2018	17/05/2018	149.89 X 151.82 X 151.09	22757	8.595	441.6	19.4	19.6
2	RCC	M20	19/04/2018	17/05/2018	151.38 X 150.97 X 150.01	22853	8.238	440.4	19.3	
3	RCC	M20	19/04/2018	17/05/2018	151.24 X 151.72 X 151.90	22947	8.060	462.1	20.1	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-04-21-03** **Date: 26/04/2018**

Customer : Assistant Executive Engineer, Byatarayanapura Sub Division, BBMP, Bangalore.

Address : Byatarayanapura Sub Division, BBMP, Bangalore.

Project Name : Improvements of roads and drains at Sandeep UnniKrishnan Nagar in Ward No.05, Byatarayanapura Sub Division.

Agency : Y.B. Ramesh, No.34, Down Bazar road, Yelahanka, Bangalore-64

Customer's Reference : EE/BTP/BBMP/E-PMT/194/2015-16

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 21-04-18

Sample ID No : 2018-04-21-03 /01

Customer ID : RCC

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M20 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 26/04/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	RCC	M20	19/04/2018	26/04/2018	151.89 X 150.89 X 151.45	22917	8.046	429.6	18.7	18.6
2	RCC	M20	19/04/2018	26/04/2018	151.04 X 151.80 X 149.82	22928	8.306	426.5	18.6	
3	RCC	M20	19/04/2018	26/04/2018	152.00 X 149.77 X 150.39	22765	8.366	420.2	18.5	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

Ward No 5

FOR CIVIL Pro.

CIVIL PRO Sig..... Date..... BANGALORE

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-04-21-03** **Date: 17/05/2018**

Customer : Assistant Executive Engineer, Byatarayanapura Sub Division, BBMP, Bangalore.

Address : Byatarayanapura Sub Division, BBMP, Bangalore.

Project Name : Improvements of roads and drains at Sandeep UnniKrishnan Nagar in Ward No.05, Byatarayanapura Sub Division.

Agency : Y.B. Ramesh, No.34, Down Bazar road, Yelahanka, Bangalore-64

Customer's Reference : EE/BTP/BBMP/E-PMT/194/2015-16

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 21-04-18

Sample ID No : 2018-04-21-03 /02

Customer ID : RCC

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M20 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 17/05/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	RCC	M20	19/04/2018	17/05/2018	150.30 X 151.27 X 151.84	22737	8.379	535.5	23.6	23.2
2	RCC	M20	19/04/2018	17/05/2018	151.33 X 150.22 X 151.32	22731	8.339	501.0	22.0	
3	RCC	M20	19/04/2018	17/05/2018	151.68 X 150.61 X 150.13	22844	7.981	548.2	24.0	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

Ward No 5

FOR CIVIL Pro.

CIVIL PRO Sig..... Date..... BANGALORE

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF PHYSICAL PROPERTIES OF CEMENT - 53 Grade

Lab ID	:	**CP-2018-04-07-16** **Date: 10-04-18**
Customer	:	Assistant Executive Engineer, Byatarayanapura Sub Division, BBMP, Bangalore.
Address	:	Byatarayanapura Sub Division, BBMP, Bangalore.
Project Name	:	Improvements of roads and drains at Sandeep UnniKrishnan Nagar in Ward No.05, Byatarayanapura Sub Division.
Agency	:	Y.B. Ramesh, No.34, Down Bazar road, Yelahanka, Bangalore-64
Customer's Reference	:	EE/BTP/BBMP/E-PMT/194/2015-16
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	07-04-18
Sample ID No	:	2018-04-07-16 /01
Sample Type	:	Birla Super 53grade
Reference to BIS codes	:	IS 12269 : 2013, 53 Grade Ordinary Portland cement Specification , IS 4031 (Part 1,2 3,4,5, 6,11):1988 IS 4031 Part 1 DETERMINATION OF FINENESS BY DRY SIEVING, Clause 4.4 IS 4031 Part 2, Determination of Fineness by Blaine Air Permeability Method, Clause 5 IS 4031 Part 3, Determination of Soundness, Clause 5,Clause 6 IS 4031 Part 4, Determination of Consistency of Standard Cement Paste, Clause 5 IS 4031 Part 5, Determination of Initial & Final Setting Time, Clause 5 IS 4031 Part 11,DETERMINATION OF DENSITY , Clause 6
Date of test	:	08-04-18
Environmental Conditions during test	:	Temperature: 26°C Humidity: 72%

Sl.No.	Physical properties	Results	Requirement as per IS 12269: 2013
1	Fineness by dry sieving (%)	2.05	–
2	Finess by Air permeablity method (m^2/kg,Min)	298.6	225m^2/kg, Min
3	Density (gm/cc)	3.13	–
4	Standard Consistency (%)	28.5%	Not specified
5	Initial Setting time	135 minutes	Not less than 30 minutes
6	Final Setting time	255 minutes	Not more than 600 minutes
7	Soundness (Le Chatelier's Method)	1.5mm	Not more than 10 mm

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

CIVIL PRO Sig..... Date..... BANGALORE

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

AS Ward No5

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Format No: CP/TF/01

TEST REPORT OF PHYSICAL PROPERTIES OF CEMENT - 53 Grade

Lab ID	:	**CP-2018-04-07-16** **Date: 05-05-18**
Customer	:	Assistant Executive Engineer, Byatarayanapura Sub Division, BBMP, Bangalore.
Address	:	Byatarayanapura Sub Division, BBMP, Bangalore.
Project Name	:	Improvements of roads and drains at Sandeep UnniKrishnan Nagar in Ward No.05, Byatarayanapura Sub Division.
Agency	:	Y.B. Ramesh, No.34, Down Bazar road, Yelahanka, Bangalore-64
Customer's Reference	:	EE/BTP/BBMP/E-PMT/194/2015-16
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	07-04-18
Sample ID No	:	2018-04-07-16 /01
Sample Type	:	Birla Super 53grade
Reference to BIS codes	:	IS 12269 : 2013, 53 Grade Ordinary Portland cement Specification , IS 4031 Part 4, Determination of Consistency of Standard Cement Paste, Clause 5 IS 4031 Part 6, Determination of Compressive Strength, Clause 6
Date of test	:	08-04-18
Environmental Conditions during test	:	Temperature: 26°C Humidity: 72%

Compressive Strength

Sl.No.	Physical properties	Results	Requirement as per IS 12269: 2013
1	3 Days	29.5N/mm^2	Not less than 27 N/mm^2
2	7 Days	39.5N/mm^2	Not less than 37 N/mm^2
3	28 Days	58.5N/mm^2	Not less than 53 N/mm^2

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

AE Ward No 5

Sig..... Date..... PIO BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT ON COARSE AGGREGATES

Lab ID	:	**CP-2018-04-07-16** **Date: 10-04-18**
Customer	:	Assistant Executive Engineer, Byatarayanapura Sub Division, BBMP, Bangalore.
Address	:	Byatarayanapura Sub Division, BBMP, Bangalore.
Project Name	:	Improvements of roads and drains at Sandeep UnniKrishnan Nagar in Ward No.05, Byatarayanapura Sub Division.
Agency	:	Y.B. Ramesh, No.34, Down Bazar road, Yelahanka, Bangalore-64
Customer's Reference	:	EE/BTP/BBMP/E-PMT/194/2015-16
Source of Sample	:	Sample supplied by Agency
Sample condition	:	Satisfactory
Date of Receipt	:	07-04-18
Sample ID No	:	2018-04-07-16 /02(a)
Sample Type	:	40mm down size coarse aggregate
Reference to BIS codes	:	IS: 383:2016 (Specification for Coarse and fine Aggregates) IS: 2386 :1963(Part - 1,3,4) RA2011 IS 2386 Part 1: Particle Size and Shape IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption IS 2386 Part 4: Mechanical Properties
Date of test		07-04-18

SIEVE ANALYSIS (PARTICLE SIZE DISTRIBUTION) OF 40MM DOWN COARSE AGGREGATE:

Total weight taken : 15000 grams

Sample No.	Sieve No.	Weight Retained in gms	Cumulative Weight Retained in gms	% Cumulative Weight Retained	% Passing	Required as per IS 383:2016
1	80 mm	0	0	0.0	100	100
2	40 mm	385	385	2.6	97.4	90-100
3	20 mm	7048	7433	49.6	50.4	30-70
4	10 mm	4396	11829	78.9	21.1	10-35
5	4.75 mm	2845	14674	97.8	2.2	0-5
6	Pan	326	15000	100.0	0	---

CIVIL PRO Sig..... Date..... BANGALORE

Format No: CP/TF/01

TEST REPORT ON COARSE AGGREGATES

Lab ID : **CP-2018-04-07-16** **Date: 10-04-18**

Sample ID No : 2018-04-07-16 /02(a)

PHYSICAL PROPERTIES

Sl.no	Tests	Result	Requirements as per IS:383-2016
1	Flakiness Index(%)	13.7	Combined Flakiness & Elongation Index Shall not Exceed 40% for Uncrushed & Crushed Aggregate
2	Elongation Index(%)	11.9	
3	Specific Gravity	2.64	_
4	Bulk Density(Loose) (Kg/l)	1.42	_
5	Bulk Density(Compacted) (Kg/l)	1.48	_
6	Water Absorption(%)	0.23	_

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL PRO Sig..... Date..... BANGALORE

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Format No: CP/TF/01

TEST REPORT ON COARSE AGGREGATES

Lab ID	:	**CP-2018-04-07-16** **Date: 10-04-18**
Customer	:	Assistant Executive Engineer, Byatarayanapura Sub Division, BBMP, Bangalore.
Address	:	Byatarayanapura Sub Division, BBMP, Bangalore.
Project Name	:	Improvements of roads and drains at Sandeep UnniKrishnan Nagar in Ward No.05, Byatarayanapura Sub Division.
Agency	:	Y.B. Ramesh, No.34, Down Bazar road, Yelahanka, Bangalore-64
Customer Reference	:	EE/BTP/BBMP/E-PMT/194/2015-16
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	07-04-18
Sample ID No	:	2018-04-07-16 /02(b)
Sample Type/ Size	:	20mm down size coarse aggregate
Reference to BIS codes	:	IS: 383:2016 (Specification for Coarse and fine Aggregates) IS: 2386 :1963(Part - 1,3,4) RA2011 IS 2386 Part 1: Particle Size and Shape IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption IS 2386 Part 4: Mechanical Properties
Date of test	:	07-04-18

SIEVE ANALYSIS (PARTICLE SIZE DISTRIBUTION) OF 20MM DOWN COARSE AGGREGATE:

Total weight taken : 5000 grams

Sample No.	Sieve No.	Weight Retained in gms	Cumulative Weight Retained in gms	% Cumulative Weight Retained	% Passing	Required as per IS 383:2016
1	40 mm	0	0	0	100	100
2	20 mm	318	318	6.4	93.6	90-100
3	10 mm	2852	3170	63.4	36.6	25-55
4	4.75 mm	1622	4792	95.8	4.2	0-10
5	Pan	208	5000	100	0	–

CIVIL PRO Sig..... Date..... BANGALORE

Format No: CP/TF/01

TEST REPORT ON COARSE AGGREGATES

Lab ID : **CP-2018-04-07-16** **Date: 10-04-18**

Sample ID No : 2018-04-07-16 /02(b)

PHYSICAL PROPERTIES

Sl.no	Tests	Result	Requirements as per IS:383-2016
1	Flakiness Index(%)	**8.9**	Combined Flakiness & Elongation Index Shall not Exceed 40% for Uncrushed & Crushed Aggregate
2	Elongation Index(%)	**10.7**	
3	Specific Gravity	**2.62**	_
4	Bulk Density(Loose) (Kg/l)	**1.45**	_
5	Bulk Density(Compacted) (Kg/l)	**1.51**	_
6	Water Absorption(%)	**0.25**	_
7	Aggregate crushing Value(%)	**23.8**	Max 30% for Aggregates to be used in concrete for wearing Surface, In case Aggregate Crushing Value Exceeds 30% then the test for ten percent fines should be conducted for Aggregates to be used in concrete other than for wearing Surface.
8	Aggregate Impact Value(%)	**22.4**	30% for Aggregates to be used in concrete for wearing Surface, 45% for Aggregates to be used in concrete other than for wearing Surface.

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signature
Quality Manager

CIVIL Pro Sig..... Date..... BANGALORE

End of Report

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF FINE AGGREGATE

Lab ID : **CP-2018-04-07-16** **Date: 10-04-18**

Customer : Assistant Executive Engineer, Byatarayanapura Sub Division, BBMP, Bangalore.

Address : Byatarayanapura Sub Division, BBMP, Bangalore.

Project Name : Improvements of roads and drains at Sandeep UnniKrishnan Nagar in Ward No.05, Byatarayanapura Sub Division.

Agency : Y.B. Ramesh, No.34, Down Bazar road, Yelahanka, Bangalore-64

Customer's Reference : EE/BTP/BBMP/E-PMT/194/2015-16

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 07-04-18

Sample ID No : 2018-04-07-16 /03

Sample Type : Fine Aggregate

Reference to BIS codes : IS 383 : 2016 (Specification for Coarse and fine Aggregates)
IS: 2386 :1963(Part - 1, 3) RA2012
IS 2386 Part 1: Particle Size and Shape
IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption

Date of test : 07-04-18

Total weight taken : 1000 grams

Sl.no	Sieve Size	Weight Retained (gms)	Cumulative Weight Retained (gms)	% Cumulative Weight Retained	% Passing	Requirement as per IS 383:2016			
						Grading Zone I	Grading Zone II	Grading Zone III	Grading Zone IV
1	10 mm	0	0	0.0	100.0	100	100	100	100
2	4.75 mm	57	57	5.7	94.3	90-100	90-100	90-100	95-100
3	2.36 mm	129	186	18.6	81.4	60-95	75-100	85-100	95-100
4	1.18 mm	219	405	40.5	59.5	30-70	55-90	75-100	90-100
5	600 micron	203	608	60.8	39.2	15-34	35-59	60-79	80-100
6	300 micron	179	787	78.7	21.3	5-20	8-30	12-40	15-50
7	150 micron	149	936	93.6	6.4	0-10	0-10	0-10	0-15
8	Pan	64	1000	100.0	0.0	---	---	---	---

Result :The tested Sample Conforms to Grading Zone II

CIVIL PRO Sig..... Date..... BANGALORE

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

TEST REPORT OF FINE AGGREGATE

Lab ID : **CP-2018-04-07-16** **Date: 10-04-18**

Sample ID No : 2018-04-07-16 /03

PHYSICAL PROPERTIES

Sl.no	Tests	Result	Requirements as per IS 383:2016
1	Water Absorption(%)	1.48	–
2	Specific Gravity	2.58	–
3	Material finer than 75 micron(%)	5.5	Uncrushed fine Aggregate Max 3%, Crushed Fine aggregate Max 15%, Mixed Fine aggregate Max 12%, Manufactured Fine aggregate Max 10%

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

AS Wash Nos

FOR CIVIL Pro.

CIVIL PRO Sig..... Date..... BANGALORE

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Format No: CP/TF/01

TEST REPORT OF PRECAST COVER SLAB

Lab ID : **CP-2018-04-19-07** **Date: 23-04-18**

Customer : Assistant Executive Engineer, Byatarayanapura Sub Division, BBMP, Bangalore.

Address : Byatarayanapura Sub Division, BBMP, Bangalore.

Project Name : Improvements of roads and drains at Sandeep UnniKrishnan Nagar in Ward No.05, Byatarayanapura Sub Division.

Agency : Y.B. Ramesh, No.34, Down Bazar road, Yelahanka, Bangalore-64

Customer's Reference : EE/BTP/BBMP/E-PMT/194/2015-16

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 19-04-18

Sample ID No : 2018-04-19-07 /04

Sample Type /Size : 100mm Thick Precast Cover Slab

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete

Date of test : 19/04/2018

Sl. No.	Identification Mark	Diameter of the core	Height of the core	Weight of the core	Area	Failure Load	Core Compressive strength	Corrected Cylinder Compressive strength	Equivalent Cube Compressive strength
		(mm)	(mm)	(kg)	(Sq.mm)	(KN)	(N/mm^2)	(N/mm^2)	(N/mm^2)
1	Cover Slab-1	75.48	100.51	1.379	4474	83.9	18.8	17.4	21.8
2	Cover Slab-2	75.51	100.49	1.386	4477	82.4	18.4	17.1	21.4
3	Cover Slab-3	75.49	100.52	1.379	4475	85.7	19.2	17.8	22.3

Note:

The results pertain to the samples received and tested.
All information furnished by the Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

CIVIL PRO Sig..... Date..... BANGALORE

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |